

ACRYLIC URETHANE SELF-SEAL SERIES M900 CLEAR

DESCRIPTION:

M900 Acrylic polyurethane is a clear, two-component self-seal product from the Verinlegno series with outstanding non-yellowing characteristics. The M900 series provides protection against UV light exposure and has excellent chemical resistance. It provides great surface hardness, moisture resistance as well as mar resistance. M900 was specifically designed for kitchen cabinets, bathroom vanities and wooden furniture.

PRODUCT DATA: PRODUCT CODE: VISCOSITY: SOLID % by WT: SOLID % by WT: VOC: DENSITY: SHEEN: SHELF LIFE:

M900 15 sec (FC#4) (application) 25% ± 2% 21 ± 2% (with catalyze) 618 g/L 0.92 gr/L 3°, 5°, 10°, 20°, 30°, 50°, 70° 12 months

MIXING RATIO: M900 ACRYLIC: B42 HARDNENER: REDUCER: POT LIFE:

DRYING TIMES: THICKNESS APPLIED: 5 parts 1 part 400-050 (30-40 %) 8 hours

APPLICATION:

Substrate should be clean, oil and grease free and well sanded. Ensure product is stirred throughly and mixted according to specifications before applying.

APPLICATION EQUIPMENT: AIR ASSIST CONVENTIONNAL FINISH THICKNESS: 4-5 we

FINISH THICKNESS: 4-5 wet mils NUMBER OF COATS: 1 or 2

TYPICAL SYSTEM:

TP WIPING STAIN: M900 Self sealed: M900 Self sealed: 1 hour dry time 1 coat 4-5 wet mils 1 coat 4-5 wet mils

STORAGE:

Store in a dry and cool area. Close the container properly after use.

DUST FREE: 1 READY TO HANDLE: 6 READY TO PACK: 1

4-5 wet mils 15 minutes 60 minutes 12 hours

Note: Drying times may vary depending on thickness applied, temperature and/or humidity.

<u>Warning:</u> Its is not recommended to use a product whose pot life has expired.



The customer is responsible for following the recommended application procedures. Failure to adhere to these specifications may result in poor appearence or failure of film. This product is for professional use only. Consult your local representative before applying with other manufacturer products. The customer should test the complete system for adhesion, compatibility and performance prior to full scale application. Please refer to the Safety Data Sheet (SDS) for safety information and precautions prior to using this product. We ONLY guarantee our product to conform to our quality. Our responsability as manufacturer is limited to the cost of the product. Please feel free to contact us at (819) 367-2201 for any further inquiries regarding this product. All information on this product data sheet is subject to change without notice.

CANLAK Inc. 674, Principale, Daveluyville, QC G0Z 1C0, QC (819) 367-2201, ON (905) 673-2936